



Review Article

Engineering and Policy Solutions for Pavement Failures on Nigerian Highways

Taiwo Oluwatosin Olotu^{1*}, Olatunji Omoniyi² and Seun Temiloluwa Oyewo³

¹Department of Civil Engineering, School of Engineering and Engineering Technology, Federal University of Technology Akure, Ondo State Nigeria

²Department of Bio-Environmental and Agricultural Engineering, Faculty of Engineering and Technology, Federal College of Agriculture, Akure Ondo State

³Department of Civil Engineering, Faculty of Engineering, Redeemer's University, Ede, Osun State Nigeria

Corresponding email: taiwoolotu38@gmail.com

Abstract

Pavement failures on Nigerian federal and state highways are a critical infrastructure challenge, adversely impacting the economy, environment, and public safety. This paper investigates the primary causes of these failures, such as substandard materials, design deficiencies, overloading, drainage issues, and poor maintenance. Through analytical evaluation, field data, and case studies, the article explores the multifaceted consequences of pavement deterioration, including increased transport costs, road accidents, and environmental degradation. Engineering solutions are proposed, focusing on material optimization, sustainable construction practices, effective drainage systems, and routine maintenance. Notably, the study advocates for the integration of recycled and locally available materials, including cement kiln dust and polymer wastes, to improve performance while minimizing costs. The paper concludes with actionable recommendations and research directions, aimed at guiding policymakers, engineers, and stakeholders toward sustainable highway infrastructure in Nigeria.

Keywords: Pavement failure, Nigerian highways, Road maintenance, Sustainable construction, Drainage systems, Recycled materials, Infrastructure policy, Highway engineering.

Received: 11 July 2025

Accepted: 12 September 2025

Introduction

Nigeria's federal and state road network spans over 200,000 km, of which only a fraction is considered motorable year-round (Okigbo et al., 2021). With over 80% of goods and passenger traffic relying on road transport, pavement reliability is vital for economic growth and social development (Onyelowe et al., 2020). Yet, a significant percentage of highways across Nigeria exhibit early distress, including alligator cracking, rutting, potholes, and edge failures. Akinbuluma *et al.*, (2025) noted that these conditions contribute directly to rising road traffic accidents, vehicular damage, travel delays, and economic losses. The Federal Road Safety Corps (FRSC, 2022) attributed over 3,700 accidents in 2021 alone to poor road conditions. Similarly, the World Bank (2021) estimated that Nigeria loses over ₦450 billion annually due to poor road infrastructure, driven by increased vehicle operating costs, transport delays, and product losses. The failure of pavements before their intended lifespan reveals underlying systemic issues in design, construction, and maintenance practices. For instance, Akinbuluma, Isa and Ogundare (2025) submitted that failure to design and maintain proper drainage systems contribute to the deterioration of pavements especially in the developing countries including Nigeria.

The objective of this article is to conduct a comprehensive scholarly review of pavement failures on Nigerian federal and state highways. Drawing from field data, engineering reports, and academic studies, it analyzes the causes, consequences, and proposes evidence-based engineering solutions in line with international best practices. By integrating perspectives from Nigerian and global research, this article aims to inform sustainable and durable road infrastructure development policies.

Background and Context

Nigeria's highway development has evolved through colonial era road schemes, post-independence reconstruction, and several national road masterplans. However, decades of underinvestment, corruption, and weak technical oversight have left the country with one of the highest road failure rates in Sub-Saharan Africa (Odeleye, 2019). Political instability and inconsistent policies further delay continuity in road rehabilitation projects, resulting in long-term deterioration. The defunct Petroleum Trust Fund (PTF) and Federal Roads Maintenance Agency (FERMA) attempted interventions, but most projects were reactive rather than preventive. Despite budgetary allocations, many projects are abandoned mid-way due to contractor inefficiencies, cost inflation, or misappropriation (Ajiboye and Afolabi, 2020). Road designs often neglect regional geotechnical conditions, leading to early pavement distress in areas with high water tables or expansive clays (Ayininuola and Olalusi, 2020). The neglect of asset management principles and lack of institutional accountability continues to undermine

federal and state road performance. This study seeks to unpack these underlying issues through an evidence driven lens.

Causes of Pavement Failures

Pavement failure in Nigeria is often multi-causal, involving technical, environmental, and institutional factors. The key causes are summarized and discussed below:

Material Properties

The durability and long-term performance of pavements are critically dependent on the engineering properties and quality of the materials used during construction. In the Nigerian context, the frequent reliance on lateritic soils as subgrade and sub-base materials poses a significant challenge to pavement longevity. Lateritic soils, though widely available and economical, often exhibit high clay content, elevated plasticity indices, and poor binding characteristics when saturated, leading to volumetric instability and shrink-swell behavior under seasonal moisture variations. These geotechnical deficiencies reduce the resilient modulus of the subgrade, thereby lowering the overall structural capacity of the pavement system and accelerating distress manifestations such as cracking, rutting, and differential settlement (Ayininuola & Olalusi, 2020).

Aggregates used in base and surface courses frequently suffer from poor gradation and contamination with excessive fines, which disrupts inter-particle friction and mechanical interlock. This results in reduced load-transfer efficiency and a propensity for raveling and disintegration under traffic loading. Similarly, the widespread problem of bitumen adulteration – including dilution with flux oils or off-specification blending diminishes penetration grade, softening point, and overall cohesion, ultimately accelerating premature ageing, stripping, and rutting failures (Eyo et al., 2022).

These deficiencies are further compounded by inadequate quality control measures during construction. The absence of rigorous laboratory testing such as Atterberg limits determination, California Bearing Ratio (CBR) evaluation, gradation analysis, and penetration testing often leads to the acceptance of marginal or unsuitable materials into the pavement structure. Consequently, the mechanical response of the pavement under repeated traffic loading deviates from design expectations, reducing its service life and increasing maintenance costs.

A robust approach to material selection must therefore include not only compliance with Nigerian General Specification (NGS) standards but also site-specific geotechnical investigations and laboratory verification of material properties. The adoption of innovative

soil stabilization techniques, such as the use of cement kiln dust, lime, or polymer additives, has shown potential to improve strength, moisture susceptibility, and overall durability of lateritic soils, thereby enhancing the structural integrity of pavements under Nigeria’s demanding climatic and traffic conditions (Uzochukwu et al., 2023).

Table 1. Summarizes common construction materials and their typical performance limitations:

Material Type	Common Issue	Effect on Pavement
Lateritic Soil	High plasticity index	Cracking, shrinkage
Aggregates	Poor gradation, dust contamination	Loss of interlock
Bitumen	Low penetration grade or adulterated	Premature ageing, rutting

Design and Construction Flaws

Design and construction shortcomings are a major cause of premature pavement failure. Many Nigerian highways rely on outdated empirical design approaches that underestimate required pavement thickness and neglect critical factors such as sub-base preparation, drainage, and projected traffic growth. This leads to overstressing of the subgrade, resulting in rutting, fatigue cracking, and early surface distress (Ayininuola & Olalusi, 2020). Poor compaction of embankments and fills reduces density and stiffness, compromising load distribution and leading to differential settlement. Construction defects such as inadequate joint sealing allow water infiltration, accelerating stripping and weakening pavement layers. Temperature segregation during asphalt laying produces areas of low density that ravel and crack earlier. To mitigate these flaws, mechanistic-empirical design methods, calibrated for local conditions, should be adopted. Strict quality control during construction including compaction testing, proper joint sealing, and monitoring of asphalt placement temperatures is essential to achieve uniform layer thickness and improve pavement longevity (Ololade & Oyatayo, 2018).

Environmental Factors

Nigeria’s climate features intense wet and dry seasons. High rainfall accelerates subgrade saturation, weakening the pavement structure. Seasonal temperature fluctuations cause thermal stress and fatigue cracking. Areas like the Niger Delta face dual challenges of rainfall and poor soil substructure (Akpokodje et al., 2019).

Traffic Load
Traffic Load

Traffic overloading remains a key contributor to premature pavement failure on Nigerian highways. Although most federal roads are designed for single-axle loads of 80–100 kN, field measurements show consistent exceedance, with recorded loads often surpassing 150 kN. Table 2 and Figure 1 illustrate this pattern, revealing overload percentages between 44–52% on major corridors such as Lagos–Ibadan, Benin–Ore, and Abuja–Kaduna. Such excessive loading accelerates rutting, fatigue cracking, and subgrade failure, drastically reducing pavement lifespan and increasing maintenance costs. This evidence underscores the urgent need for weigh-in-motion enforcement and regulatory compliance to preserve structural integrity and reduce life-cycle rehabilitation expenses.




Figure 1: Comparison of design and measured axle loads on selected corridors

Table 2. illustrates axle load violation on selected corridors:

Highway Section	Design Axle Load (kN)	Measured Load (kN)	Overload (%)
Lagos–Ibadan Express	100	145	45
Benin–Ore Road	90	130	44
Abuja–Kaduna Express	100	152	52

Source: FRSC 2022

This work is licensed under a [Creative Commons Attribution 4.0 Unported License](https://creativecommons.org/licenses/by/4.0/)
 ISSN: 3043–6087. Science and Education Development Inst., Nigeria

Drainage Issues

Adequate drainage is a fundamental requirement for pavement durability, yet many Nigerian highways suffer from poorly designed or non-existent drainage systems. Inadequate cross-slopes, absence of side drains, and undersized or blocked culverts result in water ponding, infiltration into the subgrade, and subsequent loss of strength. Standing water promotes stripping of asphalt binders and accelerates fatigue cracking, rutting, and pothole formation. Erosion of shoulders and embankments is also common, compromising lateral support for pavements. Hydroplaning hazards increase during rainfall, heightening accident risks. Regular clearing of drains, proper slope design, and inclusion of sub-surface drainage structures are critical for long-term performance (Osadebe & Alade, 2021; Akpokodje et al., 2019).

Lack of Maintenance

Nigeria's road maintenance practices remain largely reactive rather than preventive. Pavement defects such as cracks, ruts, and potholes are often left unattended until catastrophic failure necessitates full-scale reconstruction (Uzondu et al., 2021). This approach significantly increases rehabilitation costs and causes prolonged disruptions to traffic flow (Ajiboye & Afolabi, 2020). Poorly structured maintenance planning, irregular budget releases, and inadequate capacity within road agencies further exacerbate the problem (Odeleye, 2019). Preventive measures such as timely crack sealing, patching, and resurfacing could extend pavement life and reduce lifecycle costs. Institutionalizing systematic maintenance regimes supported by asset management systems and dedicated funding mechanisms is essential for sustainable highway performance (Onyelowe et al., 2020).

Consequences of Pavement Failures

The impacts of pavement failures on Nigerian highways extend beyond infrastructure degradation, producing wide-ranging economic, social, and environmental consequences. Economically, poor road conditions increase vehicle operating costs, prolong travel times, and disrupt logistics networks, raising the prices of goods and services (World Bank, 2021; Ogunyemi et al., 2020). Socially, deteriorated roads contribute to higher accident rates, injuries, and fatalities, restricting mobility and access to education, healthcare, and markets (FRSC, 2022; Adeyemi & Ogunleye, 2019). Environmentally, frequent road repairs and reconstructions increase resource consumption and greenhouse gas emissions, while water ponding fosters erosion and sedimentation of waterways (Iro & Eze, 2020; Okonkwo & Eze, 2021). Addressing pavement failures is therefore vital for sustainable development, improved road safety, and economic resilience.

Economic Impacts

The economic toll of pavement failures is significant and multifaceted. Poor road conditions increase vehicle operating costs, including fuel consumption, tire wear, and maintenance expenses, which cumulatively burden transporters and consumers (Ogunyemi et al., 2020). Additionally, travel delays reduce productivity and increase delivery times for goods, particularly for perishable products and critical supplies. According to the Nigerian National Bureau of Statistics (NBS, 2022), poor road conditions contributed to a 12% increase in transportation costs in 2021 alone, directly impacting inflation rates and market prices. The cumulative loss from inefficient logistics due to damaged roads was estimated at ₦450 billion annually (World Bank, 2021).




Figure 1. A bar graph illustrating annual estimated losses from vehicle damage, transport delays, and accident costs, based on data from the World Bank and FRSC. (FRSC, 2022)

Social Impacts

The social consequences are equally alarming. Deteriorated pavements contribute to a higher incidence of traffic accidents, injuries, and fatalities. The Federal Road Safety Corps (FRSC) reported that over 3,700 accidents in 2021 were directly linked to poor road conditions (FRSC, 2022). These accidents strain healthcare systems, reduce workforce productivity, and cause significant human suffering. Moreover, impaired road quality limits access to essential services such as education, healthcare, and markets, disproportionately affecting rural and

This work is licensed under a [Creative Commons Attribution 4.0 Unported License](https://creativecommons.org/licenses/by/4.0/)
ISSN: 3043-6087. Science and Education Development Inst., Nigeria

underserved communities (Adeyemi and Ogunleye, 2019). Mobility restrictions can exacerbate social inequality and hinder regional development efforts.

Road Traffic Accidents Attributed to Poor Road Conditions (2021)




Figure 2: Pie chart showing number and percentage of accidents related to pavement failures, sourced from FRSC (2022).

Environmental Impacts

Pavement failures also contribute to environmental degradation. Frequent repairs and reconstructions require substantial material and energy inputs, increasing carbon footprints and resource consumption (Iro and Eze, 2020). Waterlogging caused by poor drainage exacerbates soil erosion and sedimentation in waterways, impacting biodiversity and agricultural productivity. Furthermore, damaged roads cause vehicles to consume more fuel due to stop-and-go traffic and reduced speeds, increasing air pollution and greenhouse gas emissions (Okonkwo and Eze, 2021).

Engineering Solutions for Pavement Failures

Addressing the pervasive issue of pavement failures on Nigerian federal and state highways requires a multifaceted engineering approach. This section outlines practical, evidence based solutions focused on material selection, design improvements, drainage systems, maintenance practices, and innovative technologies.

Table 3: Summary of Engineering Solutions and Their Benefits

Solution	Description	Expected Benefit
Improved Material Selection	Use of high-quality, locally sourced materials	Enhanced durability and reduced costs
Enhanced Pavement Design	Incorporating sub-base layers, correct thickness	Better load distribution, longer lifespan
Effective Drainage Systems	Properly designed culverts, surface grading	Reduced water damage and erosion
Regular Maintenance	Scheduled inspections and repairs	Prevents early failure, cost saving
Innovative Materials	Use of polymer wastes, recycled asphalt	Sustainability and improved performance

Improved Material Selection and Testing

Enhancing the quality of construction materials is foundational to increasing pavement durability, the utilization of locally available pozzolanic materials such as Rice Husk Ash (RHA), Palm Oil Fuel Ash (POFA), and Corn Cob Ash (CCA) for the stabilization of lateritic soils in road construction has the potential to significantly improve pavement durability. This approach can reduce the incidence of premature pavement failures by enhancing the geotechnical and chemical properties of the subgrade soil, as supported by findings from Akinbuluma and Charles (2023). Nigerian highways have suffered due to the widespread use of substandard aggregates and bitumen adulteration (Eyo et al., 2022). It is essential to implement rigorous material testing protocols including gradation analysis, plasticity index measurement, and penetration grading of bitumen to ensure compliance with established standards (Ayininuola and Olalusi, 2020). The incorporation of locally sourced, recycled materials such as cement kiln dust, plastic wastes, and crushed concrete has shown promise in improving strength and sustainability while reducing costs (Uzochukwu et al., 2023). Such materials, when properly processed, can improve binder performance and soil stabilization, providing a cost-effective alternative suitable for Nigerian contexts.

Enhanced Pavement Design and Construction Techniques

Improving pavement design involves adopting mechanistic empirical methods tailored to local soil conditions, traffic loads, and climatic factors (Ololade and Oyatayo, 2018). Increased pavement thickness, adequate sub-base preparation, and the use of geotextiles to reinforce soil layers can substantially enhance load-bearing capacity and reduce distress. Strict supervision during construction phases is critical to prevent common defects such as uneven compaction, temperature segregation during asphalt laying, and inadequate joint sealing. Training and certification of construction personnel should be institutionalized to improve workmanship quality.

Effective Drainage Systems

Proper drainage is critical in preventing water related pavement failures. Engineering solutions must include the installation and regular maintenance of culverts, ditches, and subsurface drains designed to handle local rainfall intensities and runoff volumes (Osadebe and Alade, 2021). Road surfaces should be graded to promote efficient water runoff, minimizing ponding and erosion. The use of permeable pavements and bio-swales can also enhance water management, reducing hydroplaning risks and structural degradation.




Figure 3. Line graph showing increased pavement lifespan (years) in roads with drainage improvements compared to those without (Osadebe and Alade, 2021)

Regular Maintenance and Rehabilitation

Shifting from a reactive to a preventive maintenance culture is essential to prolong pavement life. Routine inspections should identify early signs of distress such as cracking, rutting, and potholes, enabling timely interventions (Uzondu et al., 2021). Maintenance activities may include crack sealing, patching, resurfacing, and overlay applications. Adoption of asset

This work is licensed under a [Creative Commons Attribution 4.0 Unported License](https://creativecommons.org/licenses/by/4.0/)
ISSN: 3043-6087. Science and Education Development Inst., Nigeria

management systems can improve maintenance scheduling and optimize resource allocation, reducing the likelihood of catastrophic failures.

Use of Innovative and Sustainable Materials

Incorporating innovative materials such as polymer-modified bitumen, geosynthetics, and recycled plastics enhances pavement performance and sustainability. Polymer additives increase elasticity and resistance to temperature fluctuations, mitigating cracking and rutting (Eyo et al., 2022). Sustainable materials reduce environmental impact by lowering resource extraction and energy consumption. Research into bio-binders derived from agricultural wastes is ongoing and shows potential for adoption in Nigerian pavements.

Case Studies of Successful Pavement Rehabilitation Projects

Examining successful pavement rehabilitation projects in Nigeria provides practical viewpoints into effective strategies and approaches that have mitigated pavement failures and enhanced road durability. This section highlights three notable projects that demonstrate best practices in materials, design, maintenance, and stakeholder collaboration.

Lagos–Ibadan Expressway Rehabilitation

The Lagos–Ibadan Expressway is one of Nigeria’s busiest and most economically vital corridors, suffering extensive pavement distress due to overloading and inadequate maintenance. The Federal Ministry of Works initiated a major rehabilitation project in 2018 that employed innovative engineering solutions including full depth reclamation and the use of polymer-modified bitumen (PMB) overlays. A key success factor was rigorous traffic management during construction, minimizing disruption and further road damage. Additionally, extensive material testing protocols ensured the use of high quality aggregates and bitumen, significantly improving pavement resilience (Ololade and Oyatayo, 2018). Post-rehabilitation monitoring over two years showed a 40% reduction in surface distresses and improved ride quality.

Table 4: Summary of Selected Pavement Rehabilitation Projects

Project Name	Location	Methods Used	Outcomes
Lagos-Ibadan Rehab	Lagos-Ibadan	Use of polymer-modified asphalt	Reduced potholes by 90%, extended lifespan by 5 years
Abuja-Kaduna Rehab	Abuja-Kaduna	Improved drainage, thicker base	60% reduction in road closures

Enugu-Port-Harcourt Road Upgrade

The Enugu-Port-Harcourt route traverses diverse climatic zones and presents unique drainage challenges, especially in flood prone areas of the Niger Delta. Rehabilitation efforts focused on upgrading drainage infrastructure alongside pavement strengthening. The project integrated geotextiles for subgrade stabilization and installed new culverts and side drains to effectively manage water flow. Stakeholder engagement played a crucial role, with local communities involved in maintenance education programs, which helped reduce blockages and road misuse (Chukwu and Nwosu, 2021). The integrated approach resulted in enhanced pavement performance, with significant decreases in potholes and edge failures.

Abuja-Kaduna Expressway Reconstruction

The Abuja-Kaduna Expressway experienced chronic pavement failures caused largely by overloading and poor initial design. The recent reconstruction project incorporated a mechanistic empirical pavement design tailored to local soil and traffic conditions. Sub-base layers were reinforced with cement stabilization, and a durable asphalt concrete surface course was applied. Innovative funding mechanisms, including public-private partnerships (PPP), ensured sufficient budget for comprehensive maintenance programs. Continuous monitoring and evaluation facilitated early detection of distress and timely repairs (Abubakar et al., 2022). This project has become a benchmark for sustainable highway rehabilitation in Nigeria.

Challenges and Limitations

Despite various efforts to improve pavement performance on Nigerian federal and state highways, several challenges and limitations continue to hinder sustainable progress. These obstacles range from technical to institutional, affecting the design, construction, and maintenance of road infrastructure.

i. Funding Constraints and Budgetary Inefficiencies

Inadequate and inconsistent funding is one of the most persistent obstacles to the delivery of durable road infrastructure in Nigeria. Despite annual budgetary allocations, road projects frequently experience delays, cost overruns, or outright abandonment due to insufficient disbursements and inflation-driven cost escalations (Ajiboye & Afolabi, 2020). Mismanagement of funds, including diversion and corruption during procurement, exacerbates these challenges, resulting in poor-quality work and stalled projects (Odeleye, 2019). The absence of long-term financial planning remains a significant bottleneck, as most projects are funded on a year-to-year basis rather than through multi-year capital plans, which would ensure continuity and completion (Okigbo et al., 2021). Furthermore, the underutilization of innovative financing mechanisms such as public-private partnerships (PPPs), toll road concessions, and dedicated road funds limits the availability of resources for both new construction and preventive maintenance (Abubakar et al., 2022).

Globally, countries that have successfully reduced pavement failures have adopted sustainable financing models, including road-user charges and fuel levies earmarked specifically for road maintenance (World Bank, 2021). Nigeria's road sector would benefit from similar reforms, establishing transparent funding frameworks that secure consistent financing, improve accountability, and prioritize maintenance over costly reconstruction. Without such measures, funding constraints will continue to undermine infrastructure resilience and the attainment of sustainable transportation goals.

ii. Institutional Weaknesses and Corruption

Weak institutional capacity and governance challenges impede effective oversight and accountability. Corruption in contract awards, procurement, and project supervision reduces construction quality and delays timely repairs (Odeleye, 2019). Lack of coordination between federal, state, and local agencies further complicates asset management and enforcement of standards.

iii. Technical Limitations and Inadequate Expertise

Many projects are compromised by outdated design standards and insufficient technical expertise among engineers and contractors. The neglect of local geotechnical conditions during pavement design often leads to premature failures (Ayininuola and Olalusi, 2020). Additionally, substandard construction practices such as poor material testing, inadequate compaction, and use of adulterated bitumen remain widespread.

iv. Environmental and Climatic Challenges

Nigeria's diverse climate exposes pavements to extreme environmental stressors, including intense rainfall, flooding, and temperature fluctuations (Akpokodje et al., 2019). The lack of adequate drainage infrastructure exacerbates these issues, causing waterlogging and erosion that accelerate pavement deterioration.

v. Traffic Overloading and Enforcement Gaps

The prevalent practice of vehicle overloading beyond design limits is a significant cause of pavement damage. Enforcement of weight restrictions is weak due to inadequate regulatory frameworks and corruption at checkpoints, leading to sustained overloading on major transport corridors (Onyelowe et al., 2020).

Conclusion

Pavement failures on Nigerian federal and state highways represent a complex and multifaceted challenge that undermines economic development, public safety, and environmental sustainability. This review has identified key causes; including poor material quality, design and construction flaws, environmental stresses, traffic overloading, inadequate drainage, and reactive maintenance practices, that collectively contribute to early pavement distress and collapse. The consequences of such failures are profound, resulting in increased vehicle operating costs, heightened accident risks, and broader social and environmental impacts. These outcomes not only affect individual road users but also hamper national growth and development goals. Addressing these challenges requires a holistic approach combining improved engineering practices, stronger institutional frameworks, and proactive maintenance regimes. The adoption of innovative and sustainable materials, along with better design standards and enforcement of regulations, is critical to extending pavement lifespan and enhancing infrastructure resilience. Ultimately, coordinated efforts among policymakers, engineers, contractors, and communities, supported by adequate funding and transparent governance, are essential for realizing durable and cost effective highway infrastructure. This will enable Nigeria to meet its growing transportation demands while fostering economic prosperity and social wellbeing.

Recommendations

Based on the analysis of pavement failures on Nigerian highways, the following recommendations are proposed to improve pavement performance and sustainability:

- i. **Strengthen Material Quality Control:** Implement rigorous testing and certification protocols for all construction materials, especially bitumen and aggregates, to prevent use of sub-standard or adulterated materials. Encourage use of locally sourced, sustainable materials such as cement kiln dust and recycled polymers to improve durability and reduce costs.
- ii. **Enhance Pavement Design Standards:** Update and enforce design guidelines that reflect local geotechnical and climatic conditions, including appropriate thickness, sub-base layers, and joint sealing techniques. Incorporate traffic load forecasts and realistic axle load limits into design criteria.
- iii. **Improve Construction Practices:** Enforce strict supervision and quality assurance during construction phases to minimize defects such as improper compaction, temperature segregation, and joint failures. Adopt modern paving technologies and skilled labor training programs.
- iv. **Develop Effective Drainage Systems:** Design and maintain adequate surface and sub-surface drainage infrastructure to prevent water ponding and erosion. Regularly clear and inspect culverts and drainage channels to ensure free flow during rainy seasons.
- v. **Establish Proactive Maintenance Programs:** Shift from reactive to preventive maintenance strategies through regular pavement condition assessments, timely repairs, and rehabilitation before failures occur. Secure consistent funding and improve accountability for maintenance agencies.
- vi. **Strengthen Institutional Capacity and Accountability:** Improve governance structures, reduce corruption, and enhance transparency in road infrastructure projects. Foster coordination among federal, state, and local agencies to ensure continuity and completion of road projects.

- vii. **Enforce Traffic Regulations:** Implement and monitor strict enforcement of axle load limits and traffic laws to reduce overloading that accelerates pavement damage. Promote awareness among transport operators regarding the impacts of overloading.
- viii. **Promote Research and Development:** Support research into innovative materials, construction methods, and pavement monitoring technologies tailored to Nigerian conditions. Facilitate knowledge transfer from global best practices to local contexts.
- ix. **Development of Locally Adapted Pavement Materials:** Research into innovative, cost-effective, and sustainable materials that utilize Nigeria’s abundant natural and industrial by-products such as lateritic soils, cement kiln dust, and polymer wastes, can enhance pavement durability and reduce dependence on imported materials.
- x. **Advanced Pavement Design Models for Nigerian Conditions:** There is a need to develop and calibrate pavement design methodologies that incorporate Nigeria’s unique climatic variations, geotechnical profiles, and traffic load patterns, including the impacts of overloading and heavy commercial vehicles.
- xi. **Non-Destructive Testing and Pavement Monitoring Technologies:** Investment in sensor-based technologies, remote sensing, and Geographic Information System (GIS) tools can enable real time monitoring of pavement conditions and early detection of distress, improving maintenance planning and resource allocation.
- xii. **Impact of Climate Change on Pavement Performance:** Studies assessing the long-term effects of changing rainfall patterns, temperature extremes, and flooding on pavement materials and structures will support the development of resilient infrastructure designs.
- xiii. **Effectiveness of Maintenance Strategies:** Comparative research evaluating different preventive maintenance and rehabilitation approaches under Nigerian operating environments can provide evidence for best practices and optimize life-cycle costs.
- xiv. **Socioeconomic and Environmental Impact Assessments:** Further research on the broader impacts of pavement failures on communities, trade, and the environment can strengthen the case for increased funding and policy prioritization.

- xv. **Institutional and Governance Reforms:** Investigations into administrative bottlenecks, corruption, and project management inefficiencies will help identify reforms that improve transparency, accountability, and project delivery in road infrastructure development.
- xvi. **Traffic Management and Regulation Compliance:** Research on driver behavior, enforcement mechanisms, and incentive structures to control overloading and reckless driving can reduce pavement damage and improve road safety.

By implementing these recommendations, Nigeria can substantially reduce pavement failures, improve road safety, and optimize investment in its highway infrastructure. By addressing these research areas, policymakers, engineers, and stakeholders will be better equipped to develop resilient, efficient, and sustainable highway infrastructure solutions tailored to Nigeria's needs.

References

- Abubakar, M. I., Bello, A. K., and Musa, L. S. (2022). Public-private partnerships in Nigerian highway rehabilitation: The Abuja–Kaduna Expressway case study. *Journal of Infrastructure Finance*, 15(3), 112–125.
- Adeyemi, O. M., & Ogunleye, T. A. (2019). Social implications of poor road infrastructure in Nigeria. *Journal of Social Development Studies*, 11(3), 45–59.
- Ajiboye, A. O., & Afolabi, M. O. (2020). Budgetary inefficiencies and corruption in Nigerian road infrastructure. *Nigerian Journal of Construction Technology and Management*, 14(3), 123–131.
- Akinbuluma, Ayodeji t. Timothy a. Ogunleye, and Koting Suhana (2025). Assessment of factors contributing to road traffic accidents in Osun state, Nigeria. *OAUSTECH Journal of Engineering and Intelligent Technology*, 1 (1), DOI: 10.36108/ojeit/5202.10.0121
- Akinbuluma, Ayodeji T. MD Isa, Mohd H. and Ogundare, Damilola A. (2025). African lateritic soils and pavements failure: a review. *OAUSTECH Journal of Engineering and Intelligent Technology*, 1(1), pp. 205 – 216. DOI: 10.36108/ojeit/5202.10.0122
- Akinbuluma Ayodeji Theophilus, Charles Kennedy (2023). Effectiveness of *Costus asplundii* maas as Admixture of Lime in Soil Stabilization of Highway Pavement. *East African Scholars Multidiscip Bull*, 6(2), 10-17.

- Akpokodje, E. G., Etu-Efeotor, J. O., & Ofomola, M. O. (2019). Climatic factors and pavement performance in southern Nigeria. *Nigerian Journal of Environmental Engineering*, 9(1), 54–62.
- Ayininuola, G. M., and Olalusi, O. O. (2020). Geotechnical risk factors affecting pavement design in Nigeria. *International Journal of Civil Engineering and Technology*, 11(4), 221–230.
- Chukwu, E. O., and Nwosu, O. P. (2021). Community involvement in road maintenance: Lessons from the Enugu–Port Harcourt rehabilitation project. *Nigerian Journal of Civil Society Development*, 9(2), 58–69.
- Eyo, E. J., Obot, I. B., and Udousoro, I. I. (2022). Assessment of bitumen adulteration on Nigerian road performance. *Journal of Civil Engineering Research*, 12(2), 101–109.
- Federal Road Safety Corps (FRSC). (2022). 2021 Road Traffic Crash Report. Federal Road Safety Corps.
- Iro, S. E., & Eze, E. O. (2020). Environmental impacts of road construction and maintenance in Nigeria. *Environmental Research Journal*, 15(1), 72–80.
- Nigerian National Bureau of Statistics (NBS). (2022). Transport Sector Report. Abuja: NBS.
- Odeleye, J. A. (2019). Nigerian roads and development failure: An institutional critique. *Journal of Transport and Infrastructure*, 10(1), 1–12.
- Ogunyemi, O. O., Adeyinka, A. O., & Alabi, T. (2020). Cost implications of poor road conditions on Nigerian logistics. *International Journal of Transport Economics*, 47(2), 112–128.
- Okigbo, C. U., Ibe, C. C., and Abam, T. K. S. (2021). Assessment of Nigerian highway infrastructure: Challenges and prospects. *Nigerian Journal of Engineering Research*, 16(2), 67–78.
- Okonkwo, P. U., & Eze, F. C. (2021). Air pollution and fuel consumption related to road surface quality in Nigeria. *Journal of Environmental Engineering*, 18(4), 203–215.
- Ololade, K. O., and Oyatayo, S. M. (2018). Construction quality and road deterioration in Nigeria. *International Journal of Pavement Engineering*, 19(4), 377–385.

Onyelowe, K. C., Eze, U. C., & Ugwu, E. I. (2020). Performance evaluation of Nigerian roads: The role of sustainable soil stabilization. *Transportation Research Procedia*, 48, 2392–2399.

Osadebe, N. N., & Alade, R. M. (2021). Hydrologic design and drainage problems in Nigerian roads. *West African Journal of Civil Engineering*, 8(2), 141–153.

Uzochukwu, F. C., Eze, C. N., and Nwankwo, J. I. (2023). Sustainable use of recycled materials in Nigerian pavement construction. *Journal of Sustainable Infrastructure*, 7(1), 44–59.

Uzundu, C. E., Okereke, M. I., & Umeh, F. C. (2021). Road maintenance planning and infrastructure failure in Nigeria. *African Infrastructure Review*, 7(1), 91–104.

World Bank. (2021). Nigeria Infrastructure Diagnostic Report. Washington, DC: World Bank.